

# bedra 79860

## Material Designation\*

UNS	C79860
EN	CuNi12Mn5Pb2 (CW 407 J)
JIS	/
GB	BZn12-37-1.5

## Chemical Composition

Cu	42.3-43.7	%
Pb	1.3-1.8	%
Ni	11.8-12.7	%
Mn	5.6-6.4	%
Zn	Balance	%



## Characteristics

It has excellent cutting performance with machinability equivalent to 90% of C36000, good hot workability with hot forging property equivalent to 80% of C37700, high strength, high elasticity and high corrosion resistance.

## Typical Applications

It is widely used for pen tips, guide rods and screws in pen making industry.

## Physical Properties

Density <sup>①</sup>	8.3	g/cm <sup>3</sup>
Electrical conductivity <sup>①</sup>	5	%IACS
Thermal conductivity <sup>①</sup>	30.1	W/(m·K)
Coefficient of thermal expansion <sup>②</sup>	18.3	10 <sup>-6</sup> /K
Modulus of elasticity	115	GPa

Note①: Temperature for testing is 20°C.

Note②: Temperature range for testing is 20-300°C.

## Fabrication Properties

Cold workability	Fair
Hot workability	Good
Brazing	Fair
Machinability Compared with C36000	90%

# bedra 79860

## Mechanical Properties

Diameter	Temper	Tensile Strength	Elongation	Hardness
mm		MPa min.	% min.	HV
0.5 < $\Phi$ ≤ 12	H02	550	5	140
0.5 < $\Phi$ ≤ 12	H04	650	--	170

## Tolerance and Delivery Form

### Straight Bar

Diameter	Tolerance <sup>③</sup>	Ovality	Length	Straightness	
				ft max.	mm/m max.
mm	mm	mm	mm max.		
2 ≤ $\Phi$ < 3	0.03	0.0075	2500	8.2	1.0
3 ≤ $\Phi$ < 6	0.04	0.01	2500	8.2	0.5
6 ≤ $\Phi$ < 10	0.06	0.015	4000	13.1	0.5
10 ≤ $\Phi$ < 18	0.08	0.02	4000	13.1	0.5
18 ≤ $\Phi$ < 25	0.12	0.03	4000	13.1	0.5
25 ≤ $\Phi$ < 40	0.20	0.05	4000	13.1	0.5
40 ≤ $\Phi$ < 60	0.30	0.075	4000	13.1	0.5
60 ≤ $\Phi$ < 80	0.60	0.15	3000	9.8	3.0
80 ≤ $\Phi$ < 100	1.60	0.40	2000	6.6	5.0
100 ≤ $\Phi$ ≤ 120	2.00	0.50	1500	4.9	6.0

Note③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus ( $\pm$ ), half the values given.

\*Composition                    UNS  
 Conductivity                    UNS  
 Mechanical Properties        For reference only, measured at room temperature, 68°F(20°C).  
 Fabrication Properties        UNS, Machinability for reference only.  
 Other Physical Properties      For reference only

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.