

Tellurium Copper


CTe0.5 (C14500)

Material Designation *

UNS	C14500
EN	CuTeP (CW118 C)
JIS	/
GB	TTe0.5

Chemical Composition

Cu	Balance	%
Te	0.4-0.7	%
P	0.004-0.012	%
Other	≤0.1	%



Characteristics

Tellurium copper alloy material has good free cutting performance and excellent electrical and thermal conductivity. And it has good anti-corrosion and anti-electric ablative properties. It has good cold and hot working performance, and can be forged, casted, extruded and drawn, punched and moulded. Tellurium copper is a widely used high conductivity free cutting alloy.

Physical Properties

Density ^①	8.94	g/cm ³
Melting point	1080	°C
Electrical conductivity ^①	≥85	%IACS
Thermal conductivity ^①	355	W/(m·K)
Coefficient of thermal expansion ^②	17.1	10 ⁻⁶ /K
Modulus of elasticity	117	GPa

Note①: Temperature for testing is 20°C.

Note②: Temperature range for testing is 20-300°C.

Typical Applications

It is mainly used in connector terminals, charging piles, nozzles of plasma cutting machines and power modules of communication base stations for new energy vehicles.

Fabrication Properties

Cold workability	Good
Hot workability	Good
Brazing	Good
Resistance welding	Not recommended
Hot forging compared with C37700	65%
Machinability compared with C36000	85%

CTe0.5 (C14500)

Mechanical Properties

Diameter	Temper	Tensile Strength	Yield Strength	Elongation
mm		MPa min.	MPa min.	% min.
1.5 ≤ Φ < 6.5	H02	260	205	8
	H04	330	275	4
6.5 ≤ Φ < 67	H02	260	205	12
6.5 ≤ Φ < 32	H04	305	260	8
32 ≤ Φ < 76	H04	275	240	8

Tolerance and Delivery Form

Diameter	Tolerance ^③	Straight Bar			Coil wire	
		Ovality	Length	Straightness	ID	Weight
mm	mm	mm max.	mm max.	mm/m max.	mm	kg
1.5 ≤ Φ < 6	0.05	0.02	3000	0.5	800	500
6 ≤ Φ < 10	0.06	0.03	3000	0.5	1200	800
10 ≤ Φ < 18	0.08	0.04	3000	0.5	1500	1000
18 ≤ Φ < 30	0.10	0.05	3000	0.5	--	--
30 ≤ Φ < 50	0.16	0.08	3000	0.5	--	--
50 ≤ Φ < 60	0.20	0.10	3000	0.5	--	--
60 ≤ Φ < 76	0.40	0.20	3000	2.0	--	--

Note^③: The tolerances listed in the table are specified as all plus or all minus. When tolerances are specified as plus and minus (±), half the values given.

*Composition
Conductivity
Mechanical Properties
Fabrication Properties
Other Physical Properties

ASTM B301-2013
ASTM B301-2013
ASTM B301-2013
CDA
CDA

The datasheet is for your general information only and is not subject to revision. No claim can be derived from it unless is evidence of intent or gross negligence. The data given is with reference to the relevant standards as ASTM, BS EN, JIS, RWMA, SAE and is for reference only, no warranty can be derived from the data provided. The given info may not replace the customers' own tests.